




SWSALES INC.
SAFETYWAY SALES INC./LES VENTES SAFETYWAY INC.



SAFETYWAY SALES INC./LES VENTES SAFETYWAY INC.

Marc Bouchard : 514-609-9600



PRODUCT SPECIFICATION

Powder-Free Nitrile Examination Gloves

Medical Device Licence #: 107101

Product : Non-Sterile, Ambidextrous, Finger-Textured Surface, Powder Free Nitrile Examination Gloves

Color : Light Blue

Product Code : 3501S / 3502M / 3503L / 3504XL

Grade : AQL 1.5

Standard : ASTM D6319 and ASTM D6978 Chemotherapy Drugs Test

Thickness : 3mil

| No | Test | Particular | Specification | In-house Inspection Level / AQL | |
|-------------------------|------------------------|---|--------------------------|---------------------------------|--------------------------|
| 1 | Dimension (mm) | Width | Extra Small | 75 ± 5 | S2/AQL 4.0 |
| | | | Small | 85 ± 5 | |
| | | | Medium | 95 ± 5 | |
| | | | Large | 106 ± 5 | |
| | | | Extra Large | 116 ± 5 | |
| | | | Extra Extra Large | 125 ± 5 | |
| | | Length | Min. 240 | | |
| | | Thickness (Single Wall) | Cuff (25 ± 5 from bead) | Min. 0.05 | |
| | | | Palm (center of palm) | Min. 0.07 | |
| | | | Finger (13 ± 3 from tip) | Min. 0.11 | |
| 2 | Physical Properties | Unaged (ASTM) | Tensile Strength (MPa) | Min. 14 | S2/AQL 4.0 |
| | | | Elongation at Break (%) | Min. 500 | |
| | | Unaged (EN) | Force at Break (N) | Min. 6.0 | N = 13 (Median Value) |
| | | | Aged (ASTM) | Tensile Strength (MPa) | Min. 14 |
| Elongation at Break (%) | Min. 400 | | | | |
| Aged (EN) | Force at Break (N) | Min. 6.0 | N = 13 (Median Value) | | |
| | 3 | Freedom from Holes | | | GI/AQL 1.5 |
| 4 | Visual Defects (Major) | Dirt ≥1mm ² , Sticky Pleat ≥5mm, Visible Hole (Non-Inflated), Discoloration, Mix Surface, Incomplete Beading, Wrong Orientation, Deformed Gloves | | GI/AQL 2.5 | |
| 5 | Visual Defects (Minor) | Lump <2mm ² , Dirt <1mm ² , Sticky Pleat <5mm, Poor Beading | | GI/AQL 4.0 | |
| 6 | Powder Residue | Max 2 mg/glove | | N = 5 | |

